

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

AMENDMENTS TO THE CLAIMS:

This listing of claims will replace all prior versions and listings of claims in the application.

LISTING OF CLAIMS:

1 1. (currently amended) Ink composition
2 comprising:
3 - a binder
4 - one or several dyes and/or pigments, and
5 - a solvent ionisable species,
6 in which the said solvent comprises at least 10% by
7 weight - in relation to the total weight of the ink -
8 of 1,3-dioxolane, at least 5% by weight of one or
9 several other organic compounds that can dissociate the
10 ionisable species in the ink, and less than 5% water.

1 2. (original) Ink composition according to claim
2 1, comprising from 10 to 85% by weight of dioxolane.

1 3. (previously presented) Ink composition
2 according to claim 1, comprising from 5 to 50% by
3 weight of the said other organic compounds(s).

1 4. (currently amended) Ink composition according
2 to claim 1, in which the said other organic compound(s)

3 are ~~chosen from~~ selected from the group consisting of
4 alcohols, ketones, glycol alkylene ethers and esters,
5 dimethyl formamide, N-pyrrolidone and any other
6 compounds known for their ability to dissociate
7 ionisable species and, if appropriate, their properties
8 of dissolving the other ingredients in the ink
9 composition and/or to slow down the evaporation of the
10 ink; and their mixtures.

1 5. (currently amended) Ink composition according
2 to claim 4, in which the said other compound(s) are
3 chosen from linear or branched aliphatic alcohols with
4 from 1 to 5 carbon atoms, ketones with from 3 to 10
5 carbon atoms, monoalkylic ethers ~~(in C1 to C6)~~ with 1
6 to 6 carbon atoms in the alkyl group or dialkyl ~~(in~~
7 ~~C1 to C6)~~ glycol ~~alkylenes comprising~~ ethers with 1 to 6
8 carbon atoms in each alkyl group, alkylene glycols with
9 1 to 10 carbon atoms in the alkylene chain, ~~such as~~
10 ~~ethylene glycol and propylene glycol,~~ and the esters of
11 ~~these~~ the ethers and the alkylene glycols with
12 saturated aliphatic carboxylic acids with 1 to 6 carbon
13 atoms.

1 6. (original) Ink composition according to claim
2 1, in which the said binder comprises one or several
3 resins or polymers.

1 7. (currently amended) Ink composition according
2 to claim 6, in which the said resin(s) and/or
3 polymer(s) are ~~chosen from~~ selected from the group
4 consisting of the methacrylic, vinylic, ketonic,
5 phenolic, cellulosic, styrenic, epoxy, polyurethane and
6 styrene - acrylate resins, and the combination of two
7 or more of these.

1 8. (previously presented) Ink composition
2 according to claim 1, comprising 0.1 to 30% by weight
3 of binder.

1 9. (original) Ink composition according to claim
2 1, comprising, in addition, one or several plastifiers
3 at a level of 0.1 to 20% by weight.

1 10. (original) Ink composition according to claim
2 1, in which the said solvent(s) and/or pigment(s) are
3 chosen from dyes and pigments known as "C. I. Solvent
4 Dyes" and "C. I. Pigments".

1 11. (previously presented) Ink composition
2 according to claim 1, comprising 0.1 to 20% by weight
3 of dye(s) and/or pigment(s).

1 12. (previously presented) Ink composition
2 according to claim 1, comprising, in addition, at least
3 one conductivity salt at a level of 0.1 to 20% by
4 weight.

1 13. (currently amended) Ink composition according
2 to claim 12, in which the said conductivity salt is
3 ~~chosen from~~ selected from the group consisting of
4 alkali metal salts, alkaline earth salts and single or
5 quaternary ammonium salts, in the form of halides,
6 perchlorates, nitrates, thiocyanates, formiates,
7 acetates, sulphates and propionates.

1 14. (currently amended) Ink composition according
2 to claim 1, comprising, in addition, one or several
3 additives ~~chosen from~~ selected from the group
4 consisting of anti-foaming agents, chemical
5 stabilisers, UV stabilisers, surfactants, inhibitors to
6 prevent salt corrosion, bactericides, fungicides,
7 biocides, and pH buffering agents.

1 15. (previously presented) Process for marking
2 objects by the projection of ink onto these objects,
3 whereby the projected ink is an ink composition
4 according to claim 1.

1 16. (original) Process according to claim 15,
2 whereby the marking is achieved by the technique of
3 continuous deflected ink jet.

1 17. (new) Ink according to claim 5, in which said
2 alkylene glycols are selected from the group consisting
3 of ethylene glycol and propolymer glycol.